

### Description

V-PRO 5000 (5400 Semi-Gloss) is a zero\* VOC, interior/exterior 100% acrylic semi-gloss for use on properly primed masonry, plaster, concrete, drywall, wood and metal surfaces. This product offers excellent washability, scrubability, gloss uniformity and non-blocking properties. **NOTE:** This product contains ingredients which resist the growth of microbes on the surface of the paint film.

### Recommended Uses

Designed for commercial, and institutional projects where a durable semi-gloss finish is required on new drywall, plaster, masonry, concrete, block, wood and metal surfaces. **NOT recommended for horizontal surfaces such as shelves and paneling.**

### Colors

Tintable White  
Bases: A, D & P

### Packaging

One and five gallon containers

### Finish

Semi-Gloss, sheen @ 60° = 35.0 – 45.0%

### Surface Preparation

Surfaces must be clean, dry and free from all contaminants that may impair adhesion. Glossy or slick surfaces must be scuff sanded prior to application of paint coatings and may require priming.

### Primer

|                           |   |
|---------------------------|---|
| Drywall (New):            | V-PRO 5001 Primer                               |
| Drywall (Existing):       | 4000 Uniprime<br>8000 Carefree Prime-ZALL       |
| Masonry/Concrete:         | V-PRO 5001 Primer                               |
| Wood (Interior/Exterior): | 4000 Uniprime<br>8000 Carefree Prime-ZALL       |
| Metal Non-Galvanized:     | 8600 Polytec Primer<br>9600 Protec Metal Primer |
| Metal Galvanized:         | 8600 Polytec Primer<br>4800 Metal Pro Primer    |
| Aluminum:                 | 8600 Polytec Primer                             |

### Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Light over-spray can be cleaned up with water even after drying. Clean tools and equipment with soap and water.

### Drying Time

Touch: 2 hours  
Recoat: 4 hours

### Coverage

Up to 400 square feet per gallon, depending on porosity and texture of the surface.

### Mill Thickness

Wet = 4.5      Dry = 1.8

### Thinning

Use at package consistency. If thinning is required, use water sparingly.

### Composition

|                      |              |
|----------------------|--------------|
| Titanium Dioxide     | 12.6%        |
| Extenders            | 13.6%        |
| <b>TOTAL PIGMENT</b> | <b>26.2%</b> |

|                      |              |
|----------------------|--------------|
| Acrylic Resin        | 24.3%        |
| Additives            | 11.5%        |
| Water                | 38.0%        |
| <b>TOTAL VEHICLE</b> | <b>73.8%</b> |

Weights & Measurements +/-3.0%

|                   |           |
|-------------------|-----------|
| Solids by Volume: | 40.0%     |
| Solids by Weight: | 52.4%     |
| VOC:              | <4 g/l    |
| Weight Per Gal:   | 10.5 lbs. |
| Viscosity:        | 96-102 KU |

### Conformance

**SCAQMD** - complies with Rule 1113, Architectural Coatings

**LEED** - complies with LEED 2009 and LEEDv4  
-Low Emitting Materials

**MPI** - #147

**CDPH Section 01350** - tested and passed

\*NOTE: Zero VOC is defined as no VOC containing solvents added in the manufacturing process of this product. Slight traces of VOC are present in additives used in manufacturing. This product has less than half the allowable VOC of the SCAQMD Super Compliant Coatings category.

**DISCLAIMER:** To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

Revised 06.20