

Description

A premium plus pigmented high-solids PVA sealer for new drywall and plaster. This product has very good enamel hold-out and sealing properties.

Recommended Uses

New interior drywall and plaster.

Colors

White

Packaging

One and five gallon containers

Surface Preparation

Surfaces must be clean, dry and free of all contaminants and residual dust that may impair adhesion. This product is not recommended for use over previously painted surfaces.

Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

Drying Time

Touch: 1 hour
Recoat: 4 hours

Coverage

Up to 375 square feet per gallon, depending on porosity and texture of the surface.

Mil Thickness

Wet = 4.1 Dry = 1.5

Thinning

Use at package consistency. If thinning is required, use water sparingly.

Composition

Titanium Dioxide	14.4%
Extenders	13.9%
TOTAL PIGMENT	28.3%
Vinyl Acrylic	20.0%
Additives	5.8%
Water	45.9%
TOTAL VEHICLE	71.7%

Weights & Measurements +/-3.0%

Solids by Volume:	36.6%
Solids by Weight:	50.6%
VOC:	97 g/l
Weight Per Gal:	10.73 lbs.
Viscosity:	92 KU

Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings

LEED - complies with LEED 2009 and LEEDv4
-Low Emitting Materials

CDPH Section 01350 - tested and passed

MPI - #50

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.